



Fibre specification G.657.A1

ACE-DS-OT-VSP-SM-G657A1-v03-e

date : 11-08-2020

Technical product information

Product characteristics - optical fibers

Fibre

Type of fibre	Hydrogen passivated, dispersion unshifted, matched cladding bending loss insensitive single mode fibre 9/125 µm Full compatible with G.652.D fibre Optical and geometrical properties exceed ITU-recommendations G.652.D and G.657.A1
Standard	IEC-60793-2-50, B-657.A1
Standard	ITU-T G.657.A1

Characteristics

Parameter	Properties	Unit
Mode field diameter: 1310 nm	9.0 ± 0.3	µm
Mode field diameter: 1550 nm	10.2 ± 0.4	µm
Core non-circularity	max. 6	%
Core/cladding concentricity error	max. 0.4	µm
Cladding diameter	125.0 ± 0.5	µm
Cladding non-circularity	max. 0.7	%
Coating diameter	242 ± 5	µm
Coating/cladding concentricity error	max. 8	µm
Temperature sensitivity: -60 to +85 °C	max. 0.05	dB/km
Bending sensitivity - 100 turns around Ø50 mm - 1550 nm	max. 0.05	dB
Bending sensitivity - 100 turns around Ø60 mm - 1625 nm	max. 0.05	dB
Bending sensitivity - 10 turns around Ø30 mm - 1550 nm	max. 0.1	dB
Bending sensitivity - 10 turns around Ø30 mm - 1625 nm	max. 0.3	dB
Bending sensitivity - 1 turn around Ø20 mm - 1550 nm	max. 0.75	dB
Bending sensitivity - 1 turn around Ø20 mm - 1625 nm	max. 1.5	dB
Proof test level	min. 0.70	GPa
Fibre curl	min. 4	m
Cable cut-off wavelength	max. 1260	nm
Zero-dispersion wavelength	1300 – 1324	nm
Zero-dispersion slope	max. 0.090	ps/nm ² ·km
Chromatic dispersion: 1285 nm – 1330 nm	max. 3.2	ps/nm·km
Chromatic dispersion: 1550 nm	max. 17	ps/nm·km
Chromatic dispersion: 1625 nm	max. 21	ps/nm·km
Polarisation mode dispersion: max. individual fibre	max. 0.1	ps/nm·km
PMD _Q	max. 0.06	ps/√km
Max. attenuation at 1383 nm (α ₁₃₈₃) [note a]	< max. α ₁₃₁₀	-
Effective group core refractive index: 1310 nm	1.4671	-
Effective group core refractive index: 1550 nm	1.4675	-
Effective group core refractive index: 1625 nm	1.4680	-

note a: after hydrogen ageing